



AECOMFORT COLOR

RECYCLED RUBBER RESILIENT MAT FOR THE SPORT SECTOR

Ecological mat meant to be used as finishing elastic material for fitness and power sport areas, made up of fine rubber granules coming from the recycling of ELT (end of life tyres) and colored EPDM bound by mass-polymerized polyurethanes.

ACOUSTIC PERFORMANCES

DESCRIPTION	SYMBOL	M.U.	VALUE 4mm 5mm		NORMS	NOTES
Apparent dynamic rigidity	(s' _i)	MN/m ³	66	53	UNI EN 29052-1	Internal laboratory value
Resonance frequency	(f ₀)	Hz	91	82	UNI EN 29052-1	Internal laboratory value

THERMAL PERFORMANCES

DESCRIPTION	SYMBOL	M.U.	VALUE	NORMS	NOTES
Thermal conductivity	(λ)	W/mK	0,1226	UNI EN 12667:2002	Cert.n° 025-09-the TR

PHYSICAL-MECHANICAL PERFORMANCES

DESCRIPTION	M.U.	VALUE	TOLERANCES
Rubber density	Kg/m ³	950	± 7 %
Rubber thickness	mm	3 -4 -5 – 6 -8 -10	± 10 %

DESCRIPTION	M.U.	VALUE	NORMS
Elongation percentage at break	%	60	
Tensile strength	N/mm ²	1,4	
Heat resistance	°C	Up to + 80	
Cold resistance	°C	Up to -30	
Fire rating		B2	DIN 4102
SHORE A hardness		60	



CHEMICAL PERFORMANCES

CHARACTERISTIC	PERFORMANCES
Chemical interactions	Highly resistant to acids and alkaline detergents, retains its characteristics unchanged over time
Electrostatic	Does not accumulate static charge and prevent interaction between materials
Environmental sustainability	100 % recyclable

DIMENSION AND PACKAGING

SIZE	M.U.	VALUE					
Thickness	mm	3	4	5	6	8	10
Roll height	m	1.25					
Roll length	m	17.5	15	12.5	10	8	6
Weight per m ²	Kg/m ²	2.85	3.80	4.75	5.70	7.60	9.50
Number of rolls per pallet	pz	11					
Total area per pallet	m ²	240.68	206.25	171.93	137.5	110	82.5
Pallet dimension	cm	Euro pallet					

Rev. 6 – 09/25